

ECHO



PROGETTO BAUCER S.r.l.
Via Emilia Ovest, 32/A, 42048 Rubiera (RE) Italia
Tel. +39 0522 627443 - info@progettobaucer.com
www.progettobaucer.it





ECHO

GRES PORCELLANATO SMALTATO
GLAZED PORCELAIN TILE

≡ 8,5 mm R11
20x40 cm 8"x16"



FLOOR Echo Grey 20x40 R11





FLOOR Echo White 20x40 R11





WHITE



GREY



BEIGE

ECHO

GRES PORCELLANATO SMALTATO
GLAZED PORCELAIN TILE




ECHO

FORMATI SIZES

20x40 8"x16"	Natural R11 ± 8,5 mm 15x📦 T11	OUT
14 Printings	8004881 8004882 8004883	White Grey Beige

PEZZI SPECIALI SPECIAL TRIMS

	
Battiscopa Digitale SKIRTING 9,5x40 3.7"x16" 8004911 8004912 8004913	El. a Elle Lineare Monolitico R11 MONOLITHIC L ELEMENT 15x30x4 6"x12"x1.6" 8004904 8004905 8004906
White Grey Beige	White Grey Beige

* Disponibile solo su ordinazione . Available on demand

SUGGERIMENTI DI POSA LAYING SUGGESTIONS

A diagram showing a brick pattern laid diagonally. Two bricks in the center are shaded gray. A white circle with the number '1' is in the bottom right corner.

formati sizes	pz/modulo	%/mq	pz/mq
20x40	2	100	13

A diagram showing a brick pattern laid in a herringbone (fishbone) arrangement. Two bricks in the center are shaded gray. A white circle with the number '2' is in the bottom right corner.

formati sizes	pz/modulo	%/mq	pz/mq
20x40	2	100	13

A diagram showing a brick pattern laid in a random or mixed arrangement. A cluster of six bricks in the center is shaded gray. A white circle with the number '3' is in the bottom right corner.

formati sizes	pz/modulo	%/mq	pz/mq
20x40	8	100	13

Attenzione: prodotto stonalizzato.
Si consiglia di miscelare il materiale durante la posa prelevando le piastrelle da diverse scatole.
Attention: highly shaded material.
We advise to lay material mixing tiles from different boxes.

	pz/box	mq/box	kg/box	box/pal	mq/pal	kg/pal
20x40 8"x16" Natural R11	15	1,20	20,90	64	76,80	1350,00

PROGETTO
BAUCER

CARATTERISTICHE TECNICHE TECHNICAL FEATURES

Norma Di Riferimento . Specification Reference UNI EN 14411/ISO 13006 Appendice G Bla GL

Caratteristiche tecniche Technical features	Norma Norm	ECHO
LUNGHEZZA E LARGHEZZA LENGTH AND WIDTH		CONFORME IN ACCORDANCE
SPESSORE THICKNESS		CONFORME IN ACCORDANCE
RETTILINEITÀ SPIGOLI STRAIGHTNESS OF SIDES	UNI EN ISO 10545-2	CONFORME IN ACCORDANCE
ORTOGONALITÀ RECTANGULARITY		CONFORME IN ACCORDANCE
PLANARITÀ SURFACE FLATNESS		CONFORME IN ACCORDANCE
ASPETTO ASPECT		CONFORME IN ACCORDANCE
ASSORBIMENTO D'ACQUA WATER ABSORPTION	UNI EN ISO 10545-3	≤ 0,5%
RESISTENZA A FLESSIONE FLEXURAL STRENGTH	UNI EN ISO 10545-4	≥ 35 N/mm²
MODULO DI ROTTURA BREAKING STRENGTH		≥ 1300 N
DETERMINAZIONE DELLA RESISTENZA ALL'URTO DETERMINATION OF IMPACT RESISTANCE	UNI EN ISO 10545-5	0,90
RESISTENZA ALL'ABRASIONE (METODO PEI) ABRASION RESISTANCE (PEI-METHOD)	UNI EN ISO 10545-7	DA 3 A 5 IN BASE AL COLORE FROM 3 TO 5, ACCORDING TO COLOR
COEFFICIENTE DI DILATAZIONE TERMICA LINEARE THERMAL EXPANSION COEFFICIENT	UNI EN ISO 10545-8	(5,7÷5,9) X 10 ⁻⁶ /°C
RESISTENZA AGLI SBALZI TERMICI THERMAL SHOCK RESISTANCE	UNI EN ISO 10545-9	RESISTENTE RESISTANT
DETERMINAZIONE DELLA DILATAZIONE DOVUTA ALL'UMIDITA' DETERMINATION OF MOISTURE EXPANSION	UNI EN ISO 10545-10	0,0 mm/m
DETERMINAZIONE DELLA RESISTENZA AL CAVILLO DETERMINATION OF CRAZING RESISTANCE	UNI EN ISO 10545-11	RESISTENTE RESISTANT
RESISTENZA AL GELO FROST RESISTANCE	UNI EN ISO 10545-12	INGELIVO FROST-RESISTANT
RESISTENZA AGLI AGENTI CHIMICI RESISTANCE TO CHEMICALS	UNI EN ISO 10545-13	MINIMO CLASSE B MINIMUM CLASS B
RESISTENZA ALLE MACCHIE STAIN RESISTANCE	UNI EN ISO 10545-14	MINIMO CLASSE 3 MINIMUM CLASS 3
	DIN 51130	R11
RESISTENZA ALLO SCIVOLAMENTO SLIP RESISTANCE	C.o.F B.C.R./D.M. 236 14/6/89	μ >0,40
	D.C.o.F / ANSI A326.3	>0,42
REAZIONE AL FUOCO REACTION TO FIRE	96/603/CE	A1 _{FL} /A1